PRODUCT BULLETIN

2700 Scioto Parkway Columbus, Ohio 43221 USA 614/876-0244 Fax: 614/876-0981 www.alliedmineral.com



DRI-VIBE® 985A

General Information

DRI-VIBE® 985A is a fused alumina-based dry vibratable refractory designed for lining coreless induction furnaces melting stainless and high-alloy steels. An addition of magnesia provides spinel bonding for high temperature strength. DRI-VIBE® 985A is well suited for both large and small furnaces and for use at tap temperatures ranging from 1500°C to 1710°C (2730°F to 3100°F). This product offers the following benefits and features:

- > Tolerates a wide range of scrap charge material
- > Excellent resistance to chemical attack
- > Spinel bond for high temperature thermal stability and strength

Technical Data


Chemical Analysis			
Al_2O_3	87.0%	Material Required	195 lbs./ft ³)
MgO	12.2%	Grain Size	n) and finer
CaO	0.2%	Practical Temperature Limit1815°	C (3300°F)
SiO_2	0.2%	Minimum Use Temperature1480°	C (2700°F)
Fe_2O_3	0.1%	Installation MethodDry ran	n or vibrate
		Procedure(s)	-14, CL-61

Packaged in 25 kg (55 lb.) multi-wall paper bags, protected with stretch wrap. Storage beyond 12 months is not recommended. Store in a dry location to avoid moisture pickup.

Sintering Schedule For Coreless Furnace

Sintering Data

Final Hold Temperature: 1620°C (2950°F) Sinter Rate: 222°C (400°F) /Hour



Linings Using a Consumable Form

Allied Mineral Products, Inc. supplies an entire line of monolithic refractories for the metals industry. For more information or a complete evaluation of your refractory requirements, please contact your local Allied representative.

Warning: Contains aluminum oxide, magnesium oxide, aluminosilicates, and silica. The International Agency for Research on Cancer (IARC) has classified crystalline silica inhaled in the form of quartz or cristobalite carcinogenic to humans. Refer to Material Safety Data Sheet for additional information and disposal instructions. Wear NIOSH approved respirator during installation, removal, and disposal of product to prevent inhalation of dust. In case of eye contact, flush immediately and repeatedly with water and consult a physician. For safest use and optimum performance, proper practices must be followed.

(DV985) 8/13/14 © 2014 Allied Mineral Products, Inc.