

MORTARS for STEEL

Products	Chemistry (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	
BRIKSET	40.2	52.5	1650°C (3000°F)
DURAL 65 MORTAR	65.0	27.7	1705°C (3100°F)
HC3F MORTAR	1.0	1.0	1650°C (3000°F)

