

MORTARS for HEAT TREATING & FORGING

Products	Chemistry (%)		Temp. Limit
	Al ₂ O ₃	SiO ₂	
QUICK-BOND 3000	28.5	67.2	1650°C (3000°F)
QUICK-BOND 3000 DIP MIX	28.5	67.2	1650°C (3000°F)
BRIKSET	40.2	52.5	1650°C (3000°F)
BRIKSET THICK	40.2	52.5	1650°C (3000°F)
DURAL 65 MORTAR	65	27.7	1705°C (3100°F)
DURAL 81P MORTAR	76.7	10.6	1760°C (3200°F)
DURATAB MORTAR	88.8	3.3	1815°C (3300°F)
DURATAB C MORTAR	79.3	10.1	1815°C (3300°F)
DURATAB SC MORTAR	73.4	3.6	1705°C (3100°F)
BRIKSET 711	67.1	28	1705°C (3100°F)

